







ZM 719	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
133 fili – 7x19 <i>Crociata DX – Res. 1.960 N/mm²</i>	mm.	mm.	Kg/m.	Kgf.	kN
	2	0,13	0,015	310	3,04
	3	0,20	0,035	615	6,03
	4	0,26	0,062	1.160	11,37
	4,8	0,30	0,088	1.900	18,63
	5	0,32	0,100	1.915	18,77
	6	0,40	0,150	2.600	25,49
	6,5	0,45	0,180	3.050	29,90
	7	0,47	0,210	3.615	35,44
	8	0,50	0,255	4.200	41,18
	9	0,60	0,310	5.300	51,96
	10	0,65	0,381	6.800	66,67
ZM 625	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
150 fili – 6x25+AM <i>Crociata DX – Res. 1.960 N/mm²</i>	mm.	mm.	Kg/m.	Kgf.	kN
	6	0,38	0,150	2.700	26,47
	7	0,44	0,200	3.620	35,49
	8	0,50	0,250	4.750	46,57
	9	0,56	0,330	5.960	58,43
	10	0,64	0,410	7.600	74,51
	11	0,69	0,490	9.280	90,98
	12	0,75	0,580	10.900	106,86
ZM 625 R	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
150 fili – 6x25+AM <i>Crociata DX – Res. 2.160 N/mm²</i>	mm.	mm.	Kg/m.	Kgf.	kN
	6	0,38	0,150	3.305	32,40
	7	0,44	0,200	4.010	39,31
	8	0,50	0,250	5.800	56,86
	9	0,56	0,330	7.400	72,55
	10	0,64	0,410	8.870	86,96
	11	0,69	0,490	10.100	99,02
	12	0,75	0,580	12.050	118,14
ZM 625 R-TR	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
150 fili – 6x25+AM – Trefoli Trafilati <i>Crociata DX – Res. 2.160 N/mm²</i>	mm.	mm.	Kg/m.	Kgf.	kN
	6	0,52	0,175	3.600	35,29
	7	0,61	0,245	4.900	48,04
	8	0,68	0,300	6.200	60,78
	9	0,77	0,390	7.610	74,61
	10	0,84	0,477	9.500	93,14
	11	0,90	0,583	11.380	111,57
	12	1,00	0,703	13.400	131,37
	14	0,95	0,906	17.300	169,61

ZM 636	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
216 fili – 6x36+AM Crociata DX – Res. 1.960 N/mm ²	mm.	mm.	Kg/m.	Kgf.	kN
	10	0,55	0,418	6.700	65,69
	12	0,66	0,605	9.600	94,12
	14	0,77	0,800	12.800	125,49
	16	0,90	1,130	16.500	161,76
	18	1,00	1,330	20.900	204,90
	20	1,12	1,640	25.800	252,94
	22	1,23	1,980	31.300	306,86
	24	1,35	2,350	37.100	363,73
	26	1,46	2,770	43.500	426,47
	28	1,55	3,300	50.400	494,12
	30	1,66	3,750	60.000	588,24
	32	1,78	4,250	66.800	654,90

ZM 636 R	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
216 fili – 6x36+AM Crociata DX – Res. 2.160 N/mm ²	mm.	mm.	Kg/m.	Kgf.	kN
	10	0,55	0,420	8.900	87,25
	11	0,62	0,520	10.160	99,61
	12	0,66	0,610	12.300	120,59
	13	0,72	0,700	14.200	139,22
	14	0,77	0,820	16.900	165,69
	15	0,84	0,960	18.870	185,00
	16	0,90	1,150	22.100	216,67
	17	0,94	1,230	24.260	237,84
	18	1,00	1,350	27.800	272,55
	19	1,07	1,530	31.000	303,92
	20	1,12	1,670	33.900	332,35
	22	1,23	2,020	41.000	401,96
	24	1,35	2,410	48.300	473,53
	26	1,46	2,830	56.600	554,90
	28	1,55	3,350	85.500	838,24
	30	1,66	3,800	75.600	741,18
	32	1,78	4,350	86.000	843,14

ZM 636 R-TR	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
216 fili – 6x36+AM – Tref. Trafilati Crociata DX – Res. 2.160 N/mm ²	mm.	mm.	Kg/m.	Kgf.	kN
	14	0,75	0,820	18.100	177,45
	16	0,86	1,180	23.700	232,35
	18	0,98	1,370	30.100	295,10
	20	1,07	1,700	36.950	362,25
	22	1,19	2,050	44.870	439,90
	24	1,28	2,430	53.250	522,06
	26	1,38	2,850	62.620	613,92
	28	1,53	3,380	71.105	697,11
	30	1,64	3,850	81.450	798,53
	32	1,70	4,370	92.100	902,94